Product Number: 5025G

Gray
r) 0.010 in. (0.25mm) ASTM D-3652
+/- 10%
36 yds. (108 ft.) [33M]
18.25 in. (463.55mm)
Acrylic Foam
ed Siliconized PE: 0.005" (0.13mm)
White Plastic: 3 in. ID (76.2mm) 3.25 in. OD (82.55mm)




Double Sided Acrylic Foam Tapes

Superior Quality and Adhesive Bonding Power

Extreme Bond® 5025G is a gray 10mil thick double sided closed cell pressure sensitive acrylic foam tape. The 5025G also offers an extremely powerful long-term holding capability, resists UV light, extreme temperatures & offers weather sealing abilities. The 5025G is often used in internal components and external manufacturing applications, in a wide variety of industries & applications.

Material Structure



90° Adhesion: Substrate Tested: Stainless Steel

12 inch per/minute

Speed / Load: Tape Width:

1 inch

Test Result:

12 lbs. per/inch

Dynamic Shear:

- 20min = 106.7 lbf/in2.
- 24 hours = 109.5 lbf/in²
- 48 hours = 115.2 lbf/in2
- 250 hours @ 100% RH = 108.1 lbf/in²
- 250 hours @ 176°F = 102.4 lbf/in.
- 250 hours @ -4°F = 101.0 lbf/in.

Static Shear:

(1.2677 in² overlap, held for 7 days)

- 73.4°F @ 3.3 lbs. = Passed
- 199.4°F @ 1.1 lb. = Passed

Test Methods: ASTM D3654 (Stainless Steel)

Test Method: ASTM D-3330

Test Method: ASTM D-1002



Tensile Strength:

100 lb/in² Test Method: ASTM D-897

Minimum Shelf Life: 12 months from the delivery date

(When stored in the original carton at 21°C (70°F) & 50% Relative Humidity.)

All products distributed by H&K Supplies, Inc. are guaranteed to be free from defect at the time of shipping when tested, according to H&K Supplies product specifications. The performance of the tape depends on many factors, but isn't limited to, the materials upon which the tape is being adhered to and the preparation of those materials. For the best performance use the manufacture's guidelines listed under "Application Guide" on our website, www.hksuppliesinc.com. The above figures are average values, established to our best knowledge and experience, but we recommend that you carry out your own tests to determine the suitability of specification purpose.

Please contact your Sales Representative for further details.



^{*} Available in longer lengths ** Available in larger widths